

ASKODRY

Drier formulation for water-borne alkyd resin systems

Product properties

ASKODRY 2210 and 2216 are excellent siccatives for waterborne oxidative drying alkyd resin systems, for example NECOWEL alkyd emulsions from ASK Chemicals GmbH. They are easy to emulsify in water and their special APEO-free emulsifier combination provides easy incorporation and good drying stability. The addition is made during the letdown phase.

During longer storage time the drier might settle down, this will disappear by stirring or shaking of the product again.

Application

- ASKOSRY 2210: 6 % cobalt drier; 0.8 – 2.0 % calculated on solid resin
- ASKODRY 2216: 12 % zirconium drier; 0.8 – 2.0 % calculated on solid resin

Analytical data

- ASKODRY 2210: 32 – 37 % solid content
- ASKODRY 2216: 42 – 47 % solid content

Packaging and storage

- Packaging: 25 kg cans | 170 kg drums
- Storage: store at temperatures below 30 °C; stir thoroughly before use
- Minimum shelf life: 18 months in closed original packaging
- Detailed health and safety information please find in the corresponding safety data sheet.