

# GP PHENOLIC RESIN 8900

## Thermosetting phenol resol

### Product properties

---

GP PHENOLIC RESIN 8900 is a pure self-reactive phenolic resin solution in ethanol (resol-type) with medium reactivity. The cured resin provides excellent chemical and heat resistance and especially good flame resistance combined with low smoke density.

This product is manufactured by ASK Chemicals under license agreement with Georgia Pacific

### Application

---

- Prepregs and fiber reinforces composites.

### Analytical data

---

- Form: liquid
- Solvent: ethanol
- Solid content: 60,5 – 63,5
- Viscosity, 25 °C: 170 – 230 mPa.s
- pH: 4,5 – 6,5
- B-time: 7 – 9 min

### Packaging and storage

---

- Packaging: 200 kg drum
- Transportation and storage: Keep in a cool place.
- Minimum shelf life: 2 months in closed original packaging at max. 5 °C; frozen up shelf life can be extended to six months.
- Detailed health and safety information please find in the corresponding safety data sheet.